

TECHNICAL DATA SHEET

Lytex® 4149 Engineered Structural Composite® (ESC®) Molding Compound

Lytex® 4149 is a chopped carbon fiber reinforced ESC® molding compound. It is easily moldable and provides parts that are high strength, fatigue resistant, with high heat resistance and a low density. The carbon fiber is standard modulus PAN based 3K tow.

TYPICAL PROPERTIES | UNCURED

Form and Color	Sheet, Black or Natural	Fiber Length	Nominal 1.0-inch
Carbon Fiber Content	Nominal-55% w/w	Shelf Life: @ 0°F	6 months
Resin Content	Nominal-45% w/w		

TYPICAL PROPERTIES | CURED | “Net Shape” Specimen

<u>Test</u>	<u>Procedure</u>	<u>Value</u>
Specific Gravity, g/cc	ASTM D-792	1.48
Molding Shrinkage, inch/inch (mm/mm)	ASTM D-955	<0.000 (<0.000)
Flexural Strength, psi (MPa) ¹	ASTM D-790	89,000 (613)
Flexural Modulus, psi (GPa) ¹	ASTM D-790	5.0 x10 ⁶ (34.5)
Tensile Strength, psi (MPa) ¹	ASTM D-638	42,000 (289)
Tensile Modulus, psi (GPa) ¹	ASTM D-638	8.0 x10 ⁶ (55.1)
Compression Strength, psi (MPa) ¹	ASTM D-695	40,000 (275)
Compression Modulus, psi (GPa) ¹	ASTM D-695	4.6 x10 ⁶ (31.7)
Izod Impact (notched) ft.lb./in. (J/M)	ASTM D-256	18 (960)

¹ Tensile and Flexural Properties are determined using net shape molded specimens.

TYPICAL PROPERTIES | CURED | “Machined” Specimen

<u>Test</u>	<u>Procedure</u>	<u>Value</u>
Flexural Strength, psi (MPa) ²	ASTM D-790	77,000 (531)
Flexural Modulus, psi (GPa) ²	ASTM D-790	4.6 x10 ⁶ (31.7)
Tensile Strength, psi (MPa) ²	ASTM D-3039	31,500 (217)
Tensile Modulus, psi (GPa) ²	ASTM D-3039	5.0 x10 ⁶ (34.5)
Short Beam Shear, psi (MPa) ²	ASTM D-2344	6,500 (44.8)
Shear Strength, in-plane, psi (MPa) ²	ASTM D-5379	30,000 (206)
Shear Modulus, in-plane, psi (GPa) ²	ASTM D-5379	1.6 x10 ⁶ (11)
Shear Strength, interlaminar, psi (MPa) ²	ASTM D-5379	9,500 (65.5)
Shear Modulus, interlaminar, psi (GPa) ²	ASTM D-5379	0.42 x10 ⁶ (2.9)
Coefficient of Thermal Expansion	TMA	6 µm/m°C
Glass Transition Temp. °F (°C) TanDelta	ASTM D-7028	329 (165)

² Machined Properties are determined using specimen machined from molded 12"x12" panels with 80% mold coverage.

– continued –

Data Sheet Continued

Technical Data Sheet Lytex® 4149

Note: The above cured properties are for both “Net Shape” and “Machined” specimens to respective test methods. Net shape specimens produce higher mechanical properties than machined specimens due to favorable fiber orientation in net shape molding. Established engineering practices use machined specimen data for structural analysis. Net shape specimen data represent best case, pristine properties.

Molding Suggestions – Lytex® 4149 can be molded at temperatures in the range of 280-330°F, with 310°F suggested as a starting point. Cure times will be dependent on molding temperature and part thickness and will typically be 10-15 minutes. Detailed molding suggestions are available on request. Cool molded parts at ambient temperature. A cooling fixture may be needed depending on part thickness and geometry.

Precautions – Lytex® 4149 contains carbon fibers and should be handled carefully in order to minimize skin contact. Molding areas should be well ventilated to minimize exposure to fumes. Presses must be provided with local exhaust to remove vapors from work areas. If adequate ventilation is not available, a respirator approved for removing organic vapor must be used. Care must be taken to prevent contact of carbon fibers with electrical equipment.

Typical Uncured and Cured Properties tested each lot of – Lytex® 4149:

- Fiber Content/Resin Content
- Specific Gravity
- Molding Shrinkage
- Mat Weight, (Areal Density)

Additional technical information and data on this material is available from Quantum Composites, Inc. Please contact us via phone, local representative, web site www.quantumcomposites.com or email info@quantumcomposites.com

NO WARRANTY – The above information is offered for your consideration, investigation, and verification. No warranty, expressed or implied, is given as to the materials described on this Technical Data Sheet. Quantum Composites, Inc. specifically disclaims any warranty of merchantability or fitness for any particular purpose. Final determination of the suitability of this material is the sole responsibility of the buyer. Contact our sales representative for assistance in developing procedures to fit individual requirements.

This ESC® product is generally intended to be compression molded in matched-metal die molds. Strength values may be affected by the molding process. **The values presented in this data sheet are typical values and are not to be interpreted as product specifications.**