

TECHNICAL DATA SHEET

QC 8560

Engineered Structural Composite® (ESC®) Molding Compound

QC 8560 is a vinyl ester chopped E-glass fiber reinforced ESC® molding compound. It is easily moldable and provides parts that are high strength, fatigue resistant, with high heat resistance and a low density.

TYPICAL PROPERTIES | UNCURED

Form and Color	Rolled Sheet, Black or Olive Drab	Fiber Length	Nominal 0.5-inch
Glass Fiber Content	Nominal-60% w/w	Shelf Life: @ 75°F	2 months
Resin Content	Nominal-40% w/w		

TYPICAL PROPERTIES | CURED | “Net Shape” Specimen

<u>Test</u>	<u>Procedure</u>	<u>Value</u>
Specific Gravity, g/cc	ASTM D-792	1.89
Molding Shrinkage, inch/inch (mm/mm)	ASTM D-955	<0.001 (<0.001)
Flexural Strength, psi (MPa) ¹	ASTM D-790	72,000 (496)
Flexural Modulus, psi (GPa) ¹	ASTM D-790	3.1 x10 ⁶ (21.4)
Tensile Strength, psi (MPa) ¹	ASTM D-638	41,000 (283)
Tensile Modulus, psi (GPa) ¹	ASTM D-638	3.4 x10 ⁶ (23.4)
Izod Impact (notched) ft.lb./in. (J/M)	ASTM D-256	32 (1709)

¹ Tensile and Flexural Properties determined using net shaped molded specimen

TYPICAL PROPERTIES | CURED | “Machined” Specimen

<u>Test</u>	<u>Procedure</u>	<u>Value</u>
Flexural Strength, psi (MPa) ²	ASTM D-790	61,500 (424)
Flexural Modulus, psi (GPa) ²	ASTM D-790	2.9 x10 ⁶ (20.0)
Tensile Strength, psi (MPa) ²	ASTM D-3039	30,500 (210)
Tensile Modulus, psi (GPa) ²	ASTM D-3039	3.0 x10 ⁶ (20.7)
Short Beam Shear, psi (MPa) ²	ASTM D-2344	8,000 (55.2)
Glass Transition Temp. °F (°C) TanDelta	ASTM D-7028	329 (165)

² Machined Properties are determined using specimen machined from molded 12"x12" panels with 80% mold coverage.

Note: The above cured properties are for both “Net Shape” and “Machined” specimens to respective test methods. Net shape specimens produce higher mechanical properties than machined specimens due to favorable fiber orientation in net shape molding. Established engineering practices use machined specimen data for structural analysis. Net shape specimen data represent best case, pristine properties.

– continued –

Data Sheet Continued

Technical Data Sheet QC 8560

Molding Suggestions – QC 8560 can be molded at temperatures in the range of 260-310°F, with 280°F suggested as a starting point. Cure times will be dependent on molding temperature and part thickness and will typically be 3-5 minutes. Detailed molding suggestions are available on request. Cool molded parts at ambient temperature. A cooling fixture may be needed depending on part thickness and geometry.

Precautions – QC 8560 contains glass fibers and should be handled carefully in order to minimize skin contact. Molding areas should be well ventilated to minimize exposure to fumes. Presses must be provided with local exhaust to remove vapors from work areas. If adequate ventilation is not available, a respirator approved for removing organic vapor must be used.

Typical Uncured and Cured Properties tested each lot of – QC 8560:

- Fiber Content/Resin Content
- Specific Gravity
- Molding Shrinkage
- Mat Weight, (Areal Density)

Additional technical information and data on this material is available from Quantum Composites, Inc. Please contact us via phone, local representative, web site www.quantumcomposites.com or email info@quantumcomposites.com

NO WARRANTY – The above information is offered for your consideration, investigation, and verification. No warranty, expressed or implied, is given as to the materials described on this Technical Data Sheet. Quantum Composites, Inc. specifically disclaims any warranty of merchantability or fitness for any particular purpose. Final determination of the suitability of this material is the sole responsibility of the buyer. Contact our sales representative for assistance in developing procedures to fit individual requirements.

This ESC® product is generally intended to be compression molded in matched-metal die molds. Strength values may be affected by the molding process. **The values presented in this data sheet are typical values and are not to be interpreted as product specifications.**